



TECHNICAL DATA SHEET

Order reference	HAZ99
Article number	813855

Date	5-2-08	Replaces	9-21-06	No. Pages	1
-------------	--------	-----------------	---------	------------------	---

Product Description:

Style	Pillow --“Lint-Free”
Item Size (each)	25 cm x 25 cm x 5 cm
Color	Green with green logo printing
Composition	>99% Polypropylene, < 1% Surfactant
Structure	<u>Sorbent fill:</u> Hydrophilic Green Micro-fibrous Meltblown Polypropylene (2-10 micron diameters). <u>Outer covering:</u> Spunbond polypropylene nonwoven (15-30 micron dia. fiber)
Technology	Meltblown + Spunbond
Absorbency	Hydrophilic + Oleophilic

Intended Application	Non -Linting Chemical Resistant Sorbent Pillow for Water -Base, Oil-Base, or Solvent-Base Liquids
-----------------------------	---

Absorbency Capacity	58 l per case (saturated; medium viscosity-12.5x)
----------------------------	---

Packaging Description:

Package configuration	Case	Pkg. Weight	5.26 kg
Items per Package	32-Pillows/Case	Pkg. Dimensions (approx.)	32 x 38 x 56 cm H
Container type	Carton		

Physical Properties:

<u>Parameter</u>	<u>SPC Test Method</u>	<u>Units</u>	<u>Nominal</u>	<u>Tolerance</u>
Pillow Weight	W.I.P.	kg	0.13	(+/- .03)
Absorbency** (med. oil)	SPCTM-012B	gL/gS	12.5	10-min.
Color	Visual	-----	White w/green logo	per standard

The above properties are “nominal” values used for PROCESS CONTROL when the product is produced and/or inspected. Performance “nominals” may vary depending upon the specific application, and/or the environment being applied, stored, or shipped.

**** The "Absorbency" Spec and "SPCTM012" test method is based on the protocol of ASTM F726, using SAE20 non-detergent as the Oil Type, medium viscosity.**

Attributes	Product will be free of foreign material contamination, rips, holes, and tears.
Labeling	Each package to be clearly labeled with Company Name, Address, Item No., Date, and/or Package Code (Bar Code).
Certification	Make no changes in basic process or composition without notifying customer. Claims for non-conformance of goods must be made within 60-days of delivery.